

## Report on the trial results of the fire-tunnel tests according to DIN 4102-1

Test-Nr.	01.52.4978.09	Date: 21 <sup>st</sup> April 2009
Applicant	Endutex Revestimentos Têxteis, SA ; Lugar de Baiona, 4795-784 Vilarinho STS / Portugal	
Material tested	Coated fabric	
Material name	Print SX FR	


### Material data

Test thickness	mm	Climatised storage	yes
Average surface area mass	g/m <sup>2</sup>	Preliminary end of test	no
Average raw density	kg/m <sup>3</sup>	No. of tests required for main examination	
Glow remains according to DIN 52330	%		

Test units		A	B	C	D
First flames *)	min, sec	0:04			
Max. flame height	cm	50			
Point of time *)	min, sec	0:25			
Melting point *)	min, sec	0:05			
Flames on reverse side of test unit *)	min, sec	-			
Influence on burner flame *)	min, sec	0:30			
Burning components fall down*)	min, sec	0:14			
Extent		moderate			
Continuation of burning on the perforated bottom **)	min, sec	0:15			
Max. smoke temperature	°C	115			
Appeared after *)	min, sec	10:00			
Smoke temperature after 10 min.	°C	115			
Smoke density		strong			
Glowing particles after test end **)	min, sec	-			
Remaining lengths	Test 1	cm	50		
	Test 2	cm	52		
	Test 3	cm	52		
	Test 4	cm	54		
Average value of single test		cm	52		

Remarks: ---

The test material passed the „Brandschacht“ to DIN 4102-B1.

  
ppa. Dr. Kanig

  
I. A. Maßmann

\*) Point of time referred to the test beginning  
\*\*) Time period

Art der Anforderung	Anforderungen		
	A 1	A 2	B 1
Brandschacht			
- Restlänge	> 35 cm	> 35 cm	> 15 cm
a) Mittelwert jedes Schachtes	> 20 cm	> 20 cm	> 0 cm
b) Einzelwerte	< 125 °C	< 125 °C	< 200 °C
- Rauchgastemperatur	nein	nein	zulässig
- Entflammung auf der Probenrückseite			
- Brandparallelerscheinungen			
weitere Nachweise	kein Anlass zu Bedenken 750°C Ofen, Rauchdichte, Toxizität, ggf. Heizwert		B2- Brennkasten

This information sheet is not a certificate of building material class according to DIN 4102-1.