

## Report on the trial results of the fire-tunnel tests according to DIN 4102-1

Test-Nr.	01.52.4166.06	Date: 7 <sup>st</sup> February, 2006
Applicant	Endutex Revestimentos Têxteis, S.A, Lugar de Baiona, 4795-784 Vilarinho STS	
Material tested	Coated fabric	
Material name	Print 300 FR	

### Material data

Test thickness	mm	Climatised storage	yes
Average surface area mass	g/m <sup>2</sup>	Preliminary end of test	no
Average raw density	kg/m <sup>3</sup>	No. of tests required for main examination	
Glow remains according to DIN 52330	%	Miscellaneous details :	

Test units		A	B	C	D
First flames *)	min, sec	0:04			
Max. flame height	cm	50			
Point of time *)	min, sec	0:30			
Melting point *)	min, sec	0:05			
Flames on reverse side of test unit *)	min, sec	-			
Influence on burner flame *)	min, sec	-			

Burning components fall down*)	min, sec	0:15			
Extent		Moderate			
Continuation of burning on the perforated bottom **)	min, sec	0:07			


Max. smoke temperature	°C	112			
Appeared after *)	min, sec	10:00			
Smoke temperature after 10 min.	°C	112			


Smoke density		Strong			
Glowing particles after test end **)	min, sec	-			

Remaining lengths	Test	cm	A	B	C	D
	Test 1	47				
	Test 2	50				
	Test 3	52				
	Test 4	52				
Average value of single test		50				

### Remarks:

**The test material passed the „Brandschacht“ to DIN 4102-1.**

  
ppa.Dr. Kanig

  
i. A. Maßmann

\*) Point of time referred to the test beginning  
\*\*) Time period

Art der Anforderung	Anforderungen		
	A 1	A 2	B 1
Brandschacht			
- Restlänge			
a) Mittelwert jedes Schachtes	> 35 cm	> 35 cm	> 15 cm
b) Einzelwerte	> 20 cm	> 20 cm	> 0 cm
- Rauchgastemperatur	< 125 °C	< 125 °C	< 200 °C
- Entflammung auf der Probenrückseite	nein	nein	zulässig
- Brandparallelerscheinungen	kein Anlass zu Bedenken		
weitere Nachweise	750°C Ofen, Rauchdichte, Toxizität, ggf. Heizwert	B2-Brennkasten	

This information sheet is not a certificate of building material class according to DIN 4102-1.

quick - mix Gruppe GmbH & Co. KG  
Mühlenschweg 7 ♦ 49090 Osnabrück ♦ Tel. +49 5 41 6 01-03 ♦ Fax 6 01-769

