



ENDUTEX - REVESTIMENTOS TEXTTEIS, SA

VIZELA / PORTUGAL



TECHNICAL DATA SHEET

REFERENCE: PRINT MS 74 FR

DESCRIPTION : PVC DOUBLE COATED HIGH TENACITY POLYESTER SCRIM

COMPOSITION : 57 % PVC
43 % POLYESTER

WIDTH : 160 - 250 - 320 - 500 cm

CHARACTERISTIC	SPECIFICATION	METHOD
THICKNESS (mm)	0.37	
TOTAL MASS (g/m ²)	340 ± 30	EN ISO 2286-2
FABRIC MASS (g/m ²)	145 ± 10	EN ISO 2286-2
BREAKING LOAD (daN/50mm)	L.: 240 T.: 140	EN ISO 1421
TEAR STRENGTH (daN)	L.: 50 T.: 20	DIN 53363
COLOUR FASTNESS TO LIGHT	min 6	EN ISO 105-B02
AVERAGE PERMEABILITY OF FABRIC TO AIR (l/m ² /s)	1690	EN ISO 9237
AVERAGE LIGHT TRANSMISSION	22	SF 600 Plus Spectrophotometer
BURNING BEHAVIOUR	M2	NF P92-503
BURNING BEHAVIOUR	B1	DIN 4102
BURNING BEHAVIOUR	Pass	NFPA 701
OPEN AREA (%)	11	Internal

L – Along T – Across

NOTE: This technical data sheet is not legal binding and is based on average results from current production. Unless otherwise stated, values cannot be considered as minimum to be satisfied. Purchaser is fully responsible for determining the product suitability for its intended application. Technical details are subject to change without prior notice, so please contact our technical service for any additional information you may require.

Date	Revision	QUALITY CONTROL	TECHNICAL MANAGER
2012.03.06	5		